

Chopped Strands

CS 7929



Polymer	PA, PPO	
	CS 7929* is used for reinforcement of a wide range of polyamide grades. It can also be used for reinforcement of PPO.	
Product Description	High strand integrity Excellent mechanical strength	
Technical Characteristics	Fiber Diameter (nom.)	14 µm
	Av. Fiber Length (nom.)	4,5 mm
	Glass	E-Glass (DIN 1259)
	Size	Polymeric size containing silane
	Moisture content	≤ 0,05 wt%
	Size content	approx. 0,75 wt%
	(Original data ex works)	
Packaging	Big Bag, (see detailed information on next page)	
Storage	The glass fiber should be stored in a dry place, preferably at room temperature and 50 - 70 % relative humidity.	
Contact	For further information please contact:	
	Mail	glassfiber@lanxess.com
	Phone	+49 (0)221 8885 7275

Packaging Information

CS 7929

Big Bag, recyclable

Net Weight	1000 kg
Dimensions Bag	1030 x 1030 x 1400 mm
Dimensions Pallet	1140 x 1140 mm (CP3)
Packaging Code	BD00 - FA100T
Bottom unloading through discharge spout	

**Big Bag, recyclable**

Net Weight	800 kg
Dimensions Bag.	1030 x 1030 x 1150 mm
Dimensions Pallet	1200 x 1000 mm (CP1)
Packaging Code	BD05 – FA080T
Bottom unloading through discharge spout	

**Disclaimer**

This information and our technical advice - whether verbal, in writing or by way of trials - are given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. Our advice does not release you from the obligation to verify the information currently provided - especially that contained in our safety data and technical information sheets - and to test our products as to their suitability for the intended processes and uses. The application, use and processing of our products and the products manufactured by you on the basis of our technical advice are beyond our control and, therefore, entirely your own responsibility. Our products are sold in accordance with the current version of our General Conditions of Sale and Delivery.

Values

Unless specified to the contrary, the values given have been established on standardized test. The figures should be regarded as guide values only and not as binding minimum values.