

DBD

Product Description	2,2'-dibenzamido-diphenyldisulfide (DBD)
Supply Form	light gray to beige powder

Product Characteristics

Property	Nominal Value	Unit	Test Method
Assay (of dried material)	≥ 96.5	%	ASTM D 5297 B
Final melting point	139.0 - 146.0	°C	ASTM D 1519 A
Moisture balance (100 °C)	≤ 0.5	%	ASTM D 1509 B
Sieve residue (0.063 mm)	≤ 5.0	%	ASTM D 4572

Other Product Features

Property	Typical Value
Packaging	500 kg super sacs and 18 kg paper bags
Storage Life/Conditions	2 years from date of production, keep cool (approximately 25°C) and dry in closed original packaging

Health and Safety Information: Appropriate literature has been assembled which provides information concerning the health and safety precautions that must be observed when handling the LANXESS products mentioned in this publication. For materials mentioned which are not LANXESS products, appropriate industrial hygiene and other safety precautions recommended by their manufacturers should be followed. Before working with any of these products, you must read and become familiar with the available information on their hazards, proper use, and handling. This cannot be overemphasized. Information is available in several forms, e.g., *material safety data sheets and product labels*. Consult your LANXESS Corporation representative or contact the Product Safety and Regulatory Affairs Department at LANXESS.

LANXESS Corporation, Business Unit Rhein Chemie

1588 Bushy Park Road . Goose Creek, SC 29445 . Phone: 1-800-245-7659 . www.US.LANXESS.com

The manner in which you use and the purpose to which you put and utilize our products, technical assistance and information (whether verbal, written or by way of production evaluations), including any suggested formulations and recommendations are beyond our control. Therefore, it is imperative that you test our products, technical assistance and information to determine to your own satisfaction whether they are suitable for your intended uses and applications. This application-specific analysis must at least include testing to determine suitability from a technical as well as health, safety, and environmental standpoint. Such testing has not necessarily been done by us. Unless we otherwise agree in writing, all products are sold strictly pursuant to the terms of our standard conditions of sale. All information and technical assistance is given without warranty or guarantee and is subject to change without notice. It is expressly understood and agreed that you assume and hereby expressly release us from all liability, in tort, contract or otherwise, incurred in connection with the use of our products, technical assistance, and information. Any statement or recommendation not contained herein is unauthorized and shall not bind us. Nothing herein shall be construed as a recommendation to use any product in conflict with patents covering any material or its use. No license is implied or in fact granted under the claims of any patent. As with any product, use of the products mentioned in this publication in a given application must be tested (including field testing, etc.) by the user in advance to determine suitability.

Issue number: 07 / Date of issue: June 01, 2022 / Previous issue from December 10, 2021 / Information current as of date of issue. Please contact your LANXESS representative to determine if this publication has been revised.