

# Zinkoxyd aktiv<sup>®</sup>

<b>Product Description</b>	fine particles of precipitated zinc oxide
<b>Supply Form</b>	white to slightly yellowish powder

## Product Characteristics

Property	Nominal Value	Unit	Test Method
Content of zinc oxide	≥ 93.0	%	169
Ignition loss	≤ 4.0	%	178
Sieve residue (0.063)	≤ 0.2	%	DIN ISO 787/18

## Other Product Features

Property	Typical Value
<b>Density (at 22 °C)</b>	5.68 g/cm <sup>3</sup>
<b>Specific surface area</b>	45 m <sup>2</sup> /g
<b>Volatile matter (at 110 °C)</b>	0.4 %
<b>Lead content</b>	3 ppm
<b>Cadmium content</b>	2 ppm
<b>Packaging</b>	20 kg paper bags on pallets
<b>Storage Life/Conditions</b>	18 months from date of production, keep cool (approximately 25 °C) and dry in closed original packaging
<b>Product Safety</b>	Relevant safety data and references, any necessary warning labels as well as information about the REACH registration are to be found in the EU safety data sheet.

These raw material properties are typical and, unless specifically indicated otherwise, are not to be considered as delivery specification.

Zinkoxyd aktiv<sup>®</sup> is a Registered Trademark of LANXESS Deutschland GmbH

This information and our technical advice – whether verbal, in writing or by way of trials – are given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. Our advice does not release you from the obligation to verify the information currently provided – especially that contained in our safety data and technical information sheets – and to test our products as to their suitability for the intended processes and uses. The application, use and processing of our products and the products manufactured by you on the basis of our technical advice are beyond our control and, therefore, entirely your own responsibility. Our products are sold in accordance with the current version of our General Conditions of Sale and Delivery.

Issue number: 13 / Date of issue: November 10, 2021 / Previous issue from April 28, 2017 / Information current as of date of issue. Please contact your LANXESS representative to determine if this publication has been revised.