

Datasheet

Durethan B31SK 000000

PA 6, non-reinforced, injection molding

ISO Shortname: ISO 16396-PA 6,,GR,S14-030

Property	Test Condition	Unit	Standard	guide value ¹	
				d.a.m.	cond.
Rheological properties					
C Melt volume-flow rate	260 °C; 5 kg	cm ³ /(10 min)	ISO 1133-1	110	
Molding shrinkage, parallel	150x105x3; 270 °C / WZ 80 °C; 400 bar	%	acc. ISO 294-4	0.9	
Molding shrinkage, transverse	150x105x3; 270 °C / WZ 80 °C; 400 bar	%	acc. ISO 294-4	1.1	
Post- shrinkage, parallel	150x105x3; 120 °C; 4 h	%	acc. ISO 294-4	0.15	
Post- shrinkage, transverse	150x105x3; 120 °C; 4 h	%	acc. ISO 294-4	0.15	
Mechanical properties (23 °C/50 % r. h.)					
C Tensile modulus	1 mm/min	MPa	ISO 527-1,-2	3500	1100
C Yield stress	50 mm/min	MPa	ISO 527-1,-2	85	50
C Yield strain	50 mm/min	%	ISO 527-1,-2	4.0	20
C Nominal strain at break	50 mm/min	%	ISO 527-1,-2	10	> 50
C Tensile creep modulus	1 h	MPa	ISO 899-1		900
C Tensile creep modulus	1000 h	MPa	ISO 899-1		700
C Charpy impact strength	23 °C	kJ/m ²	ISO 179-1eU	N	N
C Charpy impact strength	-30 °C	kJ/m ²	ISO 179-1eU	N	N
C Charpy notched impact strength	23 °C	kJ/m ²	ISO 179-1eA	< 10	25
C Charpy notched impact strength	-30 °C	kJ/m ²	ISO 179-1eA	< 10	< 10
Charpy notched impact strength	-40 °C	kJ/m ²	ISO 179-1eA	< 10	< 10
Izod impact strength	23 °C	kJ/m ²	ISO 180-1U	115	N
Izod impact strength	-30 °C	kJ/m ²	ISO 180-1U	116	
Izod notched impact strength	23 °C	kJ/m ²	ISO 180-1A	< 10	25
Izod notched impact strength	-30 °C	kJ/m ²	ISO 180-1A	< 10	< 10
Flexural modulus	2 mm/min	MPa	ISO 178-A	3000	900
Flexural strength	2 mm/min	MPa	ISO 178-A	120	40
Flexural strain at flexural strength	2 mm/min	%	ISO 178-A	6.0	8.0
Flexural stress at 3.5 % strain	2 mm/min	MPa	ISO 178-A	100	30
C Puncture maximum force	23 °C	N	ISO 6603-2	6100	
C Puncture maximum force	-30 °C	N	ISO 6603-2	6800	
C Puncture energy	23 °C	J	ISO 6603-2	65	
C Puncture energy	-30 °C	J	ISO 6603-2	70	
Ball indentation hardness		N/mm ²	ISO 2039-1	150	55
Thermal properties					
C Melting temperature	10 °C/min	°C	ISO 11357-1,-3	222	
C Temperature of deflection under load	1.80 MPa	°C	ISO 75-1,-2	60	

Datasheet

Durethan B31SK 000000

Property	Test Condition	Unit	Standard	guide value ¹	
				d.a.m.	cond.
C Temperature of deflection under load	0.45 MPa	°C	ISO 75-1,-2	170	
C Temperature of deflection under load	8.00 MPa	°C	ISO 75-1,-2	50	
Vicat softening temperature	50 N; 120 °C/h	°C	ISO 306	200	
C Coefficient of linear thermal expansion, parallel	23 to 55 °C	10 ⁻⁴ /K	ISO 11359-1,-2	0.7	
C Coefficient of linear thermal expansion, transverse	23 to 55 °C	10 ⁻⁴ /K	ISO 11359-1,-2	0.9	
C Burning behavior UL 94	1.5 mm	Class	UL 94	V-2	
C Burning behavior UL 94	0.4 mm	Class	UL 94	V-2	
C Oxygen index	Method A	%	ISO 4589-2	25	
Resistance to heat (ball pressure test)		°C	IEC 60695-10-2	196	
Glow wire test (GWFI)	2.0 mm	°C	IEC 60695-2-12	750	
Burning behavior US-FMVSS302	>=1.0 mm		ISO 3795	passed	
C Vicat softening temperature	50 N; 50 °C/h	°C	ISO 306	200	
Electrical properties (23 °C/50 % r. h.)					
C Relative permittivity	100 Hz	-	IEC 60250	4.0	13
C Relative permittivity	1 MHz	-	IEC 60250	3.5	4.0
C Dissipation factor	100 Hz	10 ⁻⁴	IEC 60250	60	1900
C Dissipation factor	1 MHz	10 ⁻⁴	IEC 60250	200	1000
C Volume resistivity		Ohm·m	IEC 62631-3	1E13	1E10
C Surface resistivity		Ohm	IEC 62631-3	1E15	1E14
C Electric strength	1 mm	kV/mm	IEC 60243-1	30	30
C Comparative tracking index CTI	Solution A	Rating	IEC 60112	600	
Comparative tracking index CTI M	Solution B	Rating	IEC 60112	525	(450) M
Other properties (23 °C)					
C Water absorption (Saturation value)	Water at 23 °C	%	ISO 62	10	
C Water absorption (Equilibrium value)	23 °C; 50 % RH	%	ISO 62	3	
C Density		kg/m ³	ISO 1183	1140	
Bulk density		kg/m ³	ISO 60	600	
Processing conditions for test specimens					
C Injection molding-Melt temperature		°C	ISO 294	270	
C Injection molding-Mold temperature		°C	ISO 294	80	
Processing recommendations					
Drying temperature dry air dryer		°C	-	80	
Drying time dry air dryer		h	-	2-6	
Residual moisture content		%	Acc. to Karl Fischer	0.03-0.12	
Melt temperature (Tmin - Tmax)		°C	-	260-280	

Datasheet

Durethan B31SK 000000

Property	Test Condition	Unit	Standard	guide value ¹
Mold temperature		°C	-	d.a.m. cond. 80-100

Notes

1 Typical properties: these are not to be construed as specifications

C These property characteristics are taken from the CAMPUS plastics data bank and are based on the international catalogue of basic data for plastics according to ISO 10350.

Datasheet

Durethan B31SK 000000

Disclaimer

Disclaimer for commercial products

This information and our technical advice - whether verbal, in writing or by way of trials - are given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. Our advice does not release you from the obligation to verify the information currently provided - especially that contained in our safety data and technical information sheets - and to test our products as to their suitability for the intended processes and uses. The application, use and processing of our products and the products manufactured by you on the basis of our technical advice are beyond our control and, therefore, entirely your own responsibility. Our products are sold in accordance with the current version of our General Conditions of Sale and Delivery.

Test values

Unless specified to the contrary, the values given have been established on standardized test specimens at room temperature. The figures should be regarded as guide values only and not as binding minimum values. Kindly note that, under certain conditions, the properties can be affected to a considerable extent by the design of the mould/die, the processing conditions and the coloring.

Processing note

Under the recommended processing conditions small quantities of decomposition product may be given off during processing. To preclude any risk to the health and well-being of the machine operatives, tolerance limits for the work environment must be ensured by the provision of efficient exhaust ventilation and fresh air at the workplace in accordance with the Safety Data Sheet. In order to prevent the partial decomposition of the polymer and the generation of volatile decomposition products, the prescribed processing temperatures should not be substantially exceeded. Since excessively high temperatures are generally the result of operator error or defects in the heating system, special care and controls are essential in these areas.

Conditioning

Conditioning in accordance with ISO 1110 (70 °C; 62 % r.h.)

© Envalior Deutschland GmbH | DE 40474 DUESSELDORF | Germany
