

Chopped Strands

CS 7967 (26/1493) D


Polymer
PBT, PET

CS 7967 (26/1493) D^{*} is a densified grade which can be used for reinforcement of a wide range of thermoplastic polyester grades like PBT and PET. It offers reduced bulk volume, excellent dry flowing properties and improved chop integrity (low fuzz and fines).

Product Description

Excellent mechanical strength

High strand integrity, densified, improved chop integrity

High resistance to hydrolysis

Technical
Characteristics

Fiber Diameter (nom.) 10 µm

Av. Fiber Length (nom.) 4,5 mm

Glass E-Glass (DIN 1259)

Size Polymeric size containing silane

Moisture content ≤ 0,05 wt%

Size content approx. 0,90 wt%

(Original data ex works)

Packaging

Big Bag (see detailed information on next page)

Storage

The glass fiber should be stored in a dry place, preferably at room temperature and 50 - 70 % relative humidity.

Contact

For further information please contact:

 Mail glassfiber@lanxess.com

Phone +49 (0)700 glassfiber

+49 (0)700 45277342

Packaging Information

CS 7967 (26/1493) D

Big Bag, recyclable

Net Weight	1000 kg
Dimensions Bag	870 x 870 x 1400 mm
Dimensions Pallet	1000 x 1200 mm (CP1)
Packaging Code	BC02 – FA100P
Bottom unloading through discharge spout	


Disclaimer

This information and our technical advice - whether verbal, in writing or by way of trials - are given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. Our advice does not release you from the obligation to verify the information currently provided - especially that contained in our safety data and technical information sheets - and to test our products as to their suitability for the intended processes and uses. The application, use and processing of our products and the products manufactured by you on the basis of our technical advice are beyond our control and, therefore, entirely your own responsibility. Our products are sold in accordance with the current version of our General Conditions of Sale and Delivery.

Values

Unless specified to the contrary, the values given have been established on standardized test. The figures should be regarded as guide values only and not as binding minimum values.