

Case Study

First WIT coolant pipe made of Durethan® DP AKV 30 X HR EF



Figure 1 BMW coolant pipe

HEYCO, headquartered in Remscheid, is a leading supplier of products and services for the metal and plastics processing industry. The company is a skilled provider of modules and systems for the automotive industry and its suppliers. The continuously expanding product portfolio ranges from components and modules for the bodywork and interior to high-temperature-resistant components for engine control.

Figure 1 shows the first coolant pipe made of the LANXESS plastic Durethan® DP AKV 30 X HR EF, manufactured using water injection technology (WIT). Customarily, pipes of this kind have been produced using gas injection technology (GIT). Based on experiences with GIT, water injection technology replaces the process medium gas (usually nitrogen) with water to inflate the melt in the mold. Unlike gas, water offers the advantage of high thermal conductivity, enabling significantly shorter cycle times.

Furthermore, water injection technology also enables larger diameters with lower and uniform residual wall thicknesses, thus reducing the weight of components – a crucial factor in the automotive industry.

Material:	Durethan® DP AKV 30 X HR EF
Injection molder:	HEYCO
OEM:	BMW
Industry:	Automotive

The coolant pipe shown above is used in **BMW** 4-cylinder diesel engines.

Durethan® DP AKV 30 X HR EF was specifically developed for this application. It contains 30 % of a special glass-fiber mix and offers excellent processing properties in the WIT process. The mix is vital and results in excellent inner and outer surfaces. The inner surface plays a major role in this application, as it is vital that the material does not exhibit any blisters, swirling or voids that would provide a point of attack for the medium flowing through the component and thus increase the flow resistance. In this context, Durethan® DP AKV 30 X HR EF also boasts excellent hollowing properties.

An additional strength of the material is its excellent resistance to common engine chemicals. Its hydrolysis resistance to commercial engine coolant is particularly high. In tests, the coolant pipe withstood constant media temperatures of 125 °C and short-term temperature peaks of 143 °C and therefore met the tightness and surface quality requirements. The thermoplastic also proved its long-term durability after longer periods of media contact under changing conditions at a pressure of 5 bar and temperatures of -40 to +135 °C.

LANXESS gave HEYCO extensive support in developing the coolant pipe for BMW. Its services included analyses of the material's media resistance,

pulsating compression and pressure flow tests on the prototype, and process support all the way to the start of production.

This information and our technical advice - whether verbal, in writing or by way of trials - are given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. Our advice does not release you from the obligation to verify the information currently provided - especially that contained in our safety data and technical information sheets - and to test our products as to their suitability for the intended processes and uses. The application, use and processing of our products and the products manufactured by you on the basis of our technical advice are beyond our control and, therefore, entirely your own responsibility. Our products are sold in accordance with the current version of our General Conditions of Sale and Delivery.

Trial Products (grade designations beginning with the codes DP, TP, KL or KU)

This is a Sales Product at the developmental stage (a Trial Product). For this reason, no assurances can be given as to type conformity, processability, long-term performance characteristics or other production or application parameters. No definitive statements can be made regarding the behavior of the product during processing or use. The purchaser/user uses the product entirely at his own risk. The marketing and continued supply of this material are not assured and may be discontinued at any time.

